



FUKKOL

Nourishment for
Your Machines

TECHNICAL DATA SHEET

Z300F ZINC DROSSING FLUX



Brief introduction:

Zinc alloying slag powder has strong slag disposal ability, and it is heavier than minimizing impurities. This model is suitable for smelting in large quantities or not requiring high quality products, such as polishing and electroplating.

Recommended dosage: every 100 kilograms of metal solution is about 0.4~0.80 kilogram of zinc alloying slag powder.

Matters needing attention:

1. Pay attention to the sealing and preservation